

Noble gas diffusion on metals

System	E_m [meV]	E_d [meV]	D_0 [cm^2/s]	θ	T [K]	Method	Ref.	E_b [eV]	Ref.
Xe/W(110)		50 ± 10	7×10^{-8}	0.3	50 - 70	FEM	[1]	~ 0.17	[2]
Kr/Pt(111)		~ 48	$\{1.5 \times 10^{-4}\}$	1	45	LITD	[3]	0.16	[3]
Xe/Pt(111)		50 ± 10	$3.4 \times 10^{-4 \pm 0.5}$	0.25	50 - 80	LITD	[4]	0.29	[4]
	< 9.6		-	0.05	105	QHAS	[5]		

θ is given in terms of the respective saturation coverage; estimates from original authors in {}.

References

- [1] J.-R. Chen and R. Gomer, Surf. Sci. **94**, 456 (1980).
- [2] R. Opila and R. Gomer, Surf. Sci. **112**, 1 (1981).
- [3] D. L. Meixner and S. M. George, Surf. Sci **297**, 27 (1993).
- [4] D. L. Meixner and S. M. George, J. Chem. Phys. **98**, 9115 (1993).
- [5] J. Ellis, A. P. Graham and J. P. Toennies, Phys. Rev. Lett. **82**, 5072 (1999).